



CONOSOL[®] ISOPARAFFINICS

Calumet produces highly refined, low aromatic specialty hydrocarbon fluids by carefully fractionating selected feedstocks and hydrotreating individual product streams. The chemical composition of our solvents is a complex combination of saturated hydrocarbons. These chemical properties combined with the narrow distillation ranges give our specialty hydrocarbon fluids distinct advantages in meeting environmental regulations.

The CONOSOL specialty isoparaffinic solvent line consists of both hydrotreated and straight distillate solvents produced from domestic crude with low aromatics and optimal boiling ranges.

▲ APPLICATIONS

- Adhesives
- Metalworking Fluids
- Oil Field and Drilling
- Paints and Coatings
- Sealants
- Water Treatment
- Inert carriers for herbicides and pesticides



Download a
digital copy of
this brochure.

TYPICAL PROPERTIES

PROPERTIES	METHOD	CONOSOL C-145	CONOSOL C-170	CONOSOL 170 ES	CONOSOL C-200	CONOSOL C-215	CONOSOL 260	CONOSOL 340
API Gravity @ 60 °F	ASTM D4052	48.0	42.5	40.1	42.5	48.7	39.9	34.6
Density @ 60 °F (Pounds Per Gallon)	ASTM D1250	6.563	6.770	6.865	6.770	6.533	6.873	7.092
Flash Point TCC (T), COC (C) PMCC (P) (°F)	ASTM D56, ASTM D92, ASTM D93	148 (T)	178 (P)	183 (P)	212 (P)	208 (P)	285 (P)	341 (C)
Color, Saybolt	ASTM D156	30	30	30	30	30	30	30
Refractive Index @ 25 °C	ASTM D1218	1.4347	1.4466	1.4507	1.4437	1.4510	1.4536	1.4658
Aromatics (Vol. %)	ASTM D1319	<0.5	<0.5	5	0.26	0.20	0.30	0.28
Distillation, IBP (°F)	ASTM D86	377	400	406	434	432	519	599
Distillation, 50% (°F)	ASTM D86	397	433	452	460	462	550	611
Distillation, Dry Point (°F)	ASTM D86	459	508	512	519	503	596	642
Specific Gravity @ 60/60 °F	ASTM D1250	0.7883	0.8132	0.8245	0.8131	0.7845	0.8237	0.8518
Aniline Point (°F)	ASTM D611	162.3	165.2	157.6	168.2	188.6	191	189.8
Kauri-Butanol Value	ASTM D1133	28.4	31.6	32.8	28.8	24.4	23.8	21.7
Pour Point (°F)	ASTM D97	<-80	<-80	-50	-40	-42	-30	-30
Viscosity @ 40 °C (cSt)	ASTM D445	1.46	2.08	2.15	2.30	2.01	3.74	7.86
Meets CARB Requirements	Method 310	-	-	-	Yes	Yes	Yes	Yes
Vapor Pressure @ 20 °C (mm Hg)	ASTM D2879	-	-	-	0.10	0.10	0.01	<0.01
Combustible		√	√	√				
Non-Hazardous					√	√	√	√

TECHNICAL ASSISTANCE

For product or technical questions, contact your Sales Representative or Calumet Product Support at (800) 437-3188 or email technical@calumet.com.

To the best of our knowledge, the information contained herein is accurate, but is given without warranty or guarantee. We assume no liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any information or material for the use contemplated, the name of use and whether there is any infringement of patents is the sole responsibility of the user.

Calumet's sampling and testing procedures in effect at the time of production will be used for certification testing. Results may be based on tank certification, manufacturing data, periodic testing and/or most recent product restock. Typical values only represent the values one would expect if the property were tested in our laboratories with our test methods on the specified date. Some product properties are not frequently measured, and accordingly typical values are not based on a statistically relevant number of tests.

The information in this document relates only to the named product. The user is solely responsible for all determination regarding any use and any process.



CORPORATE HEADQUARTERS

2780 Waterfront Pkwy, E. Drive • Indianapolis, IN 46214
Calumet.com • 800.437.3188 • 317.328.5660

All trademarks are owned by Calumet Refining, LLC ("Calumet"), a wholly-owned subsidiary of Calumet, Inc., unless otherwise specified.

© 2024 Calumet, Inc., All Rights Reserved.

Rev. 7/24

CUSTOMER SUPPORT
customerservice@calumet.com

PRODUCT SUPPORT
technical@calumet.com

SALES INQUIRIES
sales@calumet.com