

CALTRAN[®]

ELECTRICAL INSULATING OILS (ASTM D3487)

Calumet has more than 25 years of experience producing highly refined, clean and stable electrical insulating fluids. The CALTRAN[®] line of naphthenic transformer oils is a portfolio of customized products, formulated to fully meet specific global specifications – thus providing customers flexibility in choosing the transformer oils that meet their specific requirements. Calumet is a long-standing participant in the Annual DOBLE Survey on transformer oil.

Developed in-house by Calumet's R&D group, CALTRAN transformer oils have excellent dielectric properties, high thermal stability and good resistance to oxidation. CALTRAN transformer oils fully meet ASTM D3487 specifications for Type I and Type II mineral insulating oil in electrical apparatus.

PRODUCTS

NAPHTHENIC TYPE I	NAPHTHENIC TYPE II
CALTRAN 60-08	CALTRAN 60-15
CALTRAN N60-08	CALTRAN 60-30
	CALTRAN N60-15
	CALTRAN N60-30

PRODUCT FEATURES

- Excellent physical, chemical and electrical properties
- Good oxidation resistance
- Rapid heat transfer properties
- Outstanding low temperature properties without the need for pour point depressants
- Miscible with all comparable hydrocarbon-based transformer oils
- Meets ASTM D3487 Type I and Type II application specifications

PACKING & SHIPPING

Available in:

- Tank Truck
- Rail Car

Please inquire for drums

HANDLING & SAFETY

This product should be stored in sealed containers at ambient temperature. Read and understand the Safety Data Sheet (SDS) before using this product.

Download a digital copy of this brochure.



CALTRAN® TYPICAL PROPERTIES

PROPERTIES	METHOD	60-08	60-15	60-30	N60-08	N60-15	N60-30
Type		Type I	Type II	Type II	Type I	Type II	Type II
Viscosity @ 0 °C (cSt)	D445	48.12	46.86	49.61	47.59	48.43	48.61
Viscosity @ 40 °C (cSt)	D445	8.21	8.33	8.35	8.85	8.08	8.19
Viscosity @ 100 °C (cSt)	D445	2.21	2.21	2.23	2.31	2.19	2.19
API Gravity @ 60 °F	D4052	29.9	29.4	30.0	29.7	29.8	29.6
Density @ 15 °C Kg/dm3	D4052	0.8762	0.8791	0.8759	0.8775	0.8770	0.8777
Flash Point, COC (°C)	D92	151	152	153	149	152	149
Pour Point (°C)	D97	-62	-64	-66	-61	-62	-75
Color, ASTM	D1500	L0.5	L0.5	L0.5	L0.5	L0.5	L0.5
Aniline Point (°C)	D611	80.0	76.0	78.0	77.8	77.1	79.6
Neutralization Number (mg KOH/g)	D974	0.0002	0.002	0.003	0.007	0.002	0.003
Water Content (ppm)	D1533	10	15	5	11	10	11
Dielectric Breakdown Voltage @ 60 Hz							
Disk Electrodes, Min, kV	D877	40	42	40	39	40	39
VDE Electrodes, Min, kV 0.040-in. (1.02-mm) gap	D1816	50	31	30	49	30	31
VDE Electrodes, Min, kV 0.080-in. (2.03-mm) gap	D1816	60	60	60	60	60	59
Dielectric Breakdown Voltage, Impulse Conditions	D3300	397	300	298	300	300	299
Corrosive Sulfur	ASTM D1275B	Non-corrosive	Non-corrosive	Non-corrosive	Non-corrosive	Non-corrosive	Non-corrosive
Interfacial Tension (dyne/cm)	D971	47.9	48.7	47.0	48.0	47.8	50.6
Oxidation Stability							
72 HR Sludge, Mass%	D2440	0	0.01	0.04	0.00	0.01	0.02
72 HR Acid No., mg KOH/g	D2440	0	0.01	0.02	0.01	0.01	0.01
164 HR Sludge, Mass%	D2440	0	0.02	0.05	0.06	0.02	0.03
164 HR Acid No., mg KOH/g	D2440	0	0.01	0.02	0.00	0.01	0.01
Oxidation Inhibitor Content (Mass %)	D2668	0.06	0.18	0.26	0.06	0.17	0.26
Oxidation Stability, RPVOT (min)	D2112	-	258	265	-	265	258
Gassing Tendency (µL/min)	D2300	16	18	15	-13	-19	-21
Power Factor @ 25 °C (%)	D924	0.002	0.008	0.001	0.001	0.003	0.001
Power Factor @ 100 °C (%)	D924	0.05	0.05	0.03	0.03	0.04	0.04
PCB Content (ppm)	D4059	<1	<1	<1	<1	<1	<1
ASTM D3487 Standards		PASS	PASS	PASS	PASS	PASS	PASS

TECHNICAL ASSISTANCE

For product or technical questions, contact your Sales Representative or Calumet Product Support at (800) 437-3188 or email technical@calumet.com.

Calumet's sampling and testing procedures in effect at the time of production will be used for certification testing. Results may be based on tank certification, manufacturing data, periodic testing and/or most recent product restock. Typical values only represent the values one would expect if the property were tested in our laboratories with our test methods on the specified date. Some product properties are not frequently measured, and accordingly typical values are not based on a statistically relevant number of tests. The information in this document relates only to the named product. The user is solely responsible for all determination regarding any use and any process.

All trademarks are owned by Calumet Refining, LLC ("Calumet"), a wholly-owned subsidiary of Calumet, Inc., unless otherwise specified.

© 2024 Calumet, Inc., All Rights Reserved.

Rev. 9/24



CORPORATE HEADQUARTERS

1060 N Capitol Ave Suite 6-401 • Indianapolis IN 46204-1044
Calumet.com • 800.437.3188 • 317.328.5660

CUSTOMER SUPPORT
customerservice@calumet.com

PRODUCT SUPPORT
technical@calumet.com

SALES INQUIRIES
sales@calumet.com